

Amendments to the Specification

Please amend "Table 4" on page 24 to read as follows:

--

Table 4

Thermal properties and hydroscopicity of polyhedral oligomeric  
silsesquioxane/polyimide (PMDA-ODA) nanocomposites

	mol% of POSS in polyimide	Td ( $\mp$ °C) at 5 wt% loss	Tg ( $\mp$ °C)	Hydroscopicity (%)
Comparative	0	430.2	359.3	-
Example 1				
Example 3	10	415.1	355.1	-
Example 3	22	407.9	350.5	-
Example 3	35	405.7	337.6	-

	mol% of POSS in polyimide	Td ( $\mp$ °C) at 5 wt% loss	Tg ( $\mp$ °C)	Hydroscopicity (%)
Comparative	0	604.6	350.7	1.8
Example 1				
Example 4	5	583.7	316.6	2.0
Example 4	10	552.4	308.1	2.3
Example 4	16	534.5	303.9	1.4

--